



**TECHNICAL
DATA SHEET**

**NuCote PU GHD
Decorative Terrazzo**

PRODUCT DESCRIPTION

NuCote PU GHD is a heavy duty decorative terrazzo polyurethane trowel applied flooring system. The product incorporates anti-bacterial properties. The finish on the flooring system is a smooth polished texture, slip resistant and terrazzo colours offering good abrasion and impact resistance.

ADVANTAGES

- Decorative finish
- Chemical resistant
- Abrasion resistant
- Seamless
- Lifetime durability
- Impact resistance
- Solven free
- Temperature resistance
- Anti-bacterial properties
- Environmentally friendly
- HACCP compliant

APPLICATION AREAS

- Commercial & retail environments
- HACCP environments
- Residential environments
- Bathrooms & Ablution environments
- Odour free environments
- Processing environments
- Wet and dry areas

DESCRIPTION	RESULTS
Compressive Strength	55 N/mm ²
Tensile Strength	6.5 N/mm ²
Flexural Strength	40 N/mm ²
Bond strength	>1.5 MPa (concrete failure)
Colours	Please refer to chart
VOC	3 g/Lt
Water Absorption	<0.2 %
Elastic Mod.	1350 N/mm ²
Impact Resistance Drop Test	< 3 mm
Heavy traffic	24 hours
Light traffic	12-16 hours
Abrasion Resistance Accelerated	< 0.03 mm
Kit yield	36 L
Pot life	< 15 minutes
Coverage @ 8 – 6 mm	± 4.5 m ² per kit
Coverage @ 10 – 8 mm	± 3.6 m ² per kit

Note: The values given are average figures achieved in laboratory tests and are depending on the size of aggregate used

©Copyright 2021 in respect of this material is reserved in favor of NuCote par of RIGIFoam (Pty) Ltd and the reproduction or editing thereof is strictly prohibited.



PACKAGING

NuCote PU GHD is supplied as a three component 36 Litre kit.

STORAGE AND STABILITY

Store in a cool, dry place on pallets off the ground. Area always to be covered and avoid direct sunlight and high humidity. Shelf life is 6 months from date of manufacture in original packaging.

SURFACE PREPARATION

Remove all laitance, any previous coatings, etc. and ensure sound concrete. Diamond grind/vacu-blast the surface to create a mechanical bond onto the concrete. Remove all dust and loose debris by sweeping and then vacuuming. The surface should have a light sanded profile for the **NuCote PU GHD** system. Ensure the concrete substrate has a minimum of 25 MPa in compressive strength, 1.5 MPa in Tensile adhesion strength and less than 5 % moisture content.

PRIMING

Prime the concrete surface as per our specification with the relevant specified primer. Alternative primers are offered depending on the requirements of the substrate and environment as well as site conditions. The **NuCote GP Primer** or **NuCote PU Primer** are the most common primers. Allow to cure overnight or for at least 12 hours prior to overcoating. Maximum overcoating time of 48 hours else preparation needs to be redone to ensure a chemical and mechanical bond. Ensure application conditions are between 15 and 25°C. Should the temperature increase, an accelerated reaction can be expected. **NuCote PU Primer** must be broadcast with specified scatter aggregates onto the wet primer to assist with bonding and application.

MIXING

Ensure that all resins are mixed in the containers prior to decanting by shaking well. Decant **NuCote PU Part A** into a mixing vessel or bucket, add **NuCote PU Part B** and start mixing for 1 minute. Then add NuCote PU GHD Part C (2 aggregate bags) and continue to mix for a further 2 minutes until uniform.

PLACING

Pour onto the floor and pull evenly, float the screed using a PVC trowel. As soon as the first mix has been laid, the next mix should be prepared and placed into the previous mix. Lightly roll the surface with a mohair roller to remove any trowel marks. Make sure you roll within 8 minutes of start of each pour. Allow the screed to settle and cure for 36 hours. It is important to plan the mixing station and pouring due to the short pot life.

The grinding will then take place within 48 hours while the screed strength is at its optimum. Your first grind will be done using an 80-grit metal bound diamond bit to expose the aggregate. For your second grind you will use a 120-grit metal bound diamond bit. You need to ensure you thoroughly wash and vacuum the floor. Your last grinding stage will be done using a 150-grit metal bound diamond bit.

For your grouting stage, you need to ensure you have a damp surface. Firstly grout the floor to close any holes using **NuCote GHD Grout** and allow the grout to cure overnight. A second layer of grout is required if you have any pin holes.

Final stage will be to polish off the excess grout using a 120-grit resin bound diamond pad. The floor needs to be polished to a minimum of 200-grit. Wash and vacuum the floor thoroughly

©Copyright 2021 in respect of this material is reserved in favor of NuCote Part of RIGIFoam(Pty) Ltd and the reproduction or editing thereof is strictly prohibited.

www.nucote.co.za

+27 (0)11 974 9300



 **NuCote**[™]
FLOORING PERFECTION

DISAVOWAL: The customer acknowledges and understands that after delivery, the goods will have left the control of Rigifoam (Pty) Ltd, and that the customer will be responsible for the unpacking of and connection/installation of the goods. The customer acknowledges that it is his/her further responsibility to ensure that a fully qualified and competent person is used to install the goods to ensure their effective operation. Failure by the customer to ensure the installation of the goods, according to the written instructions of the manufacturer and/or supplier, by a fully qualified and competent person, may result in the failure of the goods, injury, loss or damages to the customer. Accordingly, and in this event, Rigifoam (Pty) Ltd accepts no responsibility for any loss or damages that might arise by reason of death or personal injury to any person engaged in the installation or use of the goods thereafter, subject to the provisions of the Consumer Protection Act 68 of 2008.

SUBSTRATE REQUIREMENTS

Concrete substrates to be a good wood float finish or a steel floated finish with a minimum Mpa compressive strength of 25 MPa. The surface must be laitance free with no dust or loose materials. The moisture content should always be monitored and be less than 5% with no rising damp. Ensure DPM's are placed under the concrete screeds.

MAINTENANCE

Use of any solvent free detergents is advised to keep the floors in good condition.

COLOURS (Customisable)

WATCH POINTS

Humidity, moisture and curing of the primers are essential to these systems. The colours are not UV stable however, functional. They may discolour when exposed to direct sunlight or UV. Storage is also vital to ensure the materials remain in a workable condition.

DISCLAIMER

Colours will always vary according to the printed version on our literature. These products are sold according to our standard terms and conditions of sale which is available on request and may not be overridden by any other legal documentation. Whilst the information contained herein is true, accurate and represents our best knowledge, the user must contact NuCote immediately should any complications occur. Site conditions, labour and application issues are out of our control and the contractor holds this liability. Figures for consumption are estimates and theoretical and do not allow for wastage, surface profiles that are not up to standard, porosity, variations in levels etc.

SAFETY AND HANDLING

Please read the Materials safety datasheet as supplied by us for this product to ensure compliance with the OHSA NO. 85 of 1993 act. The finished system is not hazardous to health or environment.

HEALTH AND SAFETY INFORMATION

In the case of contact with eyes, rinse immediately with plenty of water and seek medical advice. If inhaled move to fresh air. Consult a physician after significant exposure. If swallowed, clean mouth with water and drink afterwards plenty of water. Do not induce vomiting without medical advice. In case of skin contact, take off contaminated clothing and shoes immediately. Wash off with soap and plenty of water. Consult a physician when in contact with existing open wounds.

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological, and other safety-related data.

The **Material Safety Data** applicable to the handling of urethane raw materials should be read, understood, and rigidly adhered to. These are available on request from **NuCote**.

In accordance with ISO 9001:2015 and the Occupational Health and Safety Act (Act 85 of 1993), herewith Product and Safety Data Sheet.	
We hereby confirm that we have received a Product and Safety Data Sheet for NuCote PU GHD system and are returning the obsolete copies.	
COMPANY NAME:	
SIGNATURE:	
NAME:	
DATE:	

CAUTION

The information contained in this bulletin is to the best of our knowledge true and accurate but any recommendations or suggestions, which may be made, are without guarantee since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

